

(11)Publication number : 10-312088  
(43)Date of publication of application : 24.11.1998

G03G 9/09  
G03G 9/087  
G03G 15/01

(71)Applicant : FUJI XEROX CO LTD

(72)Inventor : TAKE MICHIO  
HASHIMOTO MASAKI  
TANIGUCHI SHUICHI

(57)Abstract:

**SOLUTION:** This toner compsn. consists of at least a binder resin and a coloring agent, and the binder resin consists of a polyester resin having 2500 to 4500 number average mol.wt., 7000 to 30000 weight average mol.wt., 95 to 120° C softening point and 60 to 75° C glass transition temp. As for the coloring agent, C.I.Pigment Red 122 and C.I.Pigment Red 57:1 are used for the magenta toner, C.I.Pigment Blue 15:3 is used for the cyan toner, and C.I.Pigment Yellow 180 is used for the yellow toner. The coloring agent of the toner preferably contains a product by flashing treatment essentially comprising the polyester resin above described and the color pigments above described, or high-density pigment pellets.

[Date of request for examination] 15.08.2001

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number] 3436067

[Date of registration] 3436067  
[Date of registration] 06.06.2003

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]

Copyright (C); 1998,2003 Japan Patent Office